

**SPECIFICATION FOR 50/125 MULTIMODE OPTICAL FIBER: ISO/IEC 11801, IEC 60793-2-10
Type A1a.1 and ITU-T RECOMMENDATION G.651.1 SPECIFICATION**

OPTICAL PROPERTIES

Attenuation	@ 850 nm @ 1300 nm	≤ 2.8 dB/km ≤ 0.8 dB/km
Overfilled Modal Bandwidth	@ 850 nm @ 1300 nm	≥ 500 MHz.km ≥ 800 MHz.km
Numerical Aperture		0.200 ± 0.015
Attenuation Uniformity	Point or Step Defects Extended Variations	≤ 0.2 dB ≤ 0.2 dB
Group Index of Refraction	850 nm (Typical) 1300 nm	1.482 1.477

MACROBENDING PROPERTIES

100 Turns Around 75mm Diameter	@850 nm	≤0.5 dB/km
100 Turns Around 75mm Diameter	@1300 nm	≤0.5 dB/km

GEOMETRICAL PROPERTIES

Core	50 ± 2 µm
Core Non-Circularity	≤ 5.0 %
Core/Cladding Concentricity Error	≤ 1 µm
Cladding Diameter	125.0 ± 1.0 µm
Cladding Non-Circularity	≤ 0.7 %
Coating Diameter	245 ± 10 µm
Coating Concentricity Error	≤ 12.5 µm
Coating Non-Circularity	≤ 6 %

MECHANICAL PROPERTIES

Proof Test Level	≥ 0.69 GPa / ≥ 1.0 %
------------------	----------------------

*“Leviton is **dedicated to designing, developing and manufacturing** sustainable **high performance** structured cabling and specialty **cabling solutions.**”*

The information contained in this document is valid and correct at the time of issue. Leviton reserves the right to modify details without notice in light of subsequent standard/specification changes and ongoing technical developments.